

PRODUCING PLANTS: SEATTLE, LONG BEACH, ANTIOCH, REDWOOD CITY,

Produced from San Marcos rock in two types. Crusher run as produced through swing hammer mills and screened hammer mill product with the fines removed. Redwood City has open storage which necessitates the use of a rotary dryer when rock has become wet.

PRODUCT SPECIFICATIONS	Crusher Run Gypsum Rock	Screened Gypsum Rock	Test Procedures
Free Water (% Maximum)	0.8	1.0	T - 6.23
Purity (% Gypsum Minimum)*	95.0	95.0	T - 6
SO <sub>3</sub> (% Minimum)	44.2	44.2	(ASTM-C471)
Size Gradation			
Plus 1 inch	None	None	
Minus 1 inch Plus 1/4 inch	No Maximum	98% Minimum	
Minus 1/4 inch	No Maximum	2% Maximum	

\* If purity as % gypsum drops below specifications due to presence of anhydrite, the SO<sub>3</sub> minimum of 44.2% shall prevail as a basis for acceptance or rejection.